

12.01.2000

What is claimed is:

Sub
A1

1. A polyurethane which has a number average
molecular weight M_n of from 3,000 to 50,000 and an
acid number of from 10 to 35 and is preparable by
reacting
- (a1) at least one polyesterpolyol having a
number average molecular weight M_n of from
1,000 to 4,000, an acid number of from 0 to
15, and an OH number of from 35 to 150,
based on acyclic aliphatic and cyclo-
aliphatic dicarboxylic acids,
- (a2) a mixture of at least one diol and one
triol,
- (a3) at least one compound containing at least
two isocyanate-reactive functional groups
(a31) and at least one functional group
(a32) capable of forming anions, and
- (a4) a mixture of at least one acyclic
aliphatic and at least one cycloaliphatic
diisocyanate,

with the proviso that

Sub
Cont
A1

(i) in the mixture (a2) the diols and triols are in a molar ratio of from 2 : 1 to 13 : 1,

5 (ii) the molar ratio of the polyesterpolyols (a1) to the mixture (a2) is from 4.5 : 1 to 1 : 1, and

10 (iii) in the mixture (a4) the acyclic aliphatic and cycloaliphatic diisocyanates are in a molar ratio of from 1 : 0.16 to 1 : 6;

15 to give an isocyanato-containing prepolymer which is then chain extended with a polyfunctional amine or amino alcohol and, if desired, is neutralized.

2. A polyurethane dispersion comprising

20 (A) at least one polyurethane as claimed in claim 1

(B) in dispersion in an aqueous medium.

25 3. The use of the polyurethane as claimed in claim 1 or the polyurethane dispersion as claimed in claim 2 in plastics finishing.

Sub
cont
A1

4. The use of the polyurethane as claimed in claim 1 or the polyurethane dispersion as claimed in claim 2 in an aqueous coating material.

5 5. The use of the polyurethane as claimed in claim 1 or the polyurethane dispersion as claimed in claim 2 in an aqueous coating material, said material further comprising color and/or effect pigments (C).

10

6. The use of the polyurethane as claimed in claim 1 or the polyurethane dispersion as claimed in claim 2 in an aqueous coating material, said material further comprising coatings additives (D).

15

7. The use of the polyurethane as claimed in claim 1 or the polyurethane dispersion as claimed in claim 2 in an aqueous coating material for plastics finishing.

20

Sub
A2

8. The use of the polyurethane as claimed in claim 1 or the polyurethane dispersion as claimed in claim 2 in plastics finishing, wherein the plastics finish is obtained by the steps of

25

(I) applying a two component waterbased primer and curing it to give a primer coat,

sub
cont
A2

(II) applying an aqueous coating material to the primer coat,

(III) applying a two component clearcoat material wet on wet, and

(IV) curing the resultant basecoat/clearcoat film.

A3
total

[illegible]